

FACULTY OF ENGINEERING

DEPARTMENT OF POLYMER TEXTILE AND INDUSTRIAL ENGINEERING

FINAL YEAR PROJECT REPORT

DEVELOPMENT OF A LUFFA FIBER/ PLA BIO COMPOSITE MATERIAL FOR INDOOR WALL PARTITIONING APPLICATIONS

BY

OCHAR JAMES

BU/UP/2019/1800

Email 1: ocharjames13@gmail.com

AND

NAMBOZO SARAH GIFT BU/UP/2019/1787

Email 2: nambozosarah680@gmail.com

A final year project report submitted to the department of polymer textile and industrial engineering at Busitema University in partial fulfillment of the requirement for the award of a bachelor's degree in polymer textile and industrial engineering

SEPTEMBER 2023

ABSTRACT

This is an outline for a project proposal report that was done at Busitema University between June 2023 and August 2023 for the second semester of the fourth year. The study reveals the potential of luffa fiber as a workable reinforcement for PLA matrix, providing a promising avenue for the creation of ecologically friendly and sustainable bio composites with enhanced performance properties. Utilizing the compression molding technique, luffa fiber was chemically treated and combined with PLA to create samples of Bio composite materials. The physical properties such as water absorption, moisture content and mechanical properties such as tensile strength, flexural strength a generated Bio composites are anticipated to be assessed. The research project intends to give engineering students the fundamental abilities needed to become competent as well as a fascinating look into engineering activities.

ACKNOWLEDGEMENT

We greatly thank the almighty God who enabled us to implement this project as well as the gift of life and strength that enabled us fully participate in the final year project. Special thanks goes to our lecturers (Mr Tigalana Dan, Dr Kamalha Edwin and Dr Nibikora Ildephonse) who dedicated their time to impart different research ideas and guide us until the day of presentation. Also special thanks to Head of department, Polymer textile and Industrial Engineering Dr Kamalha Edwin (PhD), Busitema University for organizing and overseeing to ensure that project research was conducted well.

LIST OF ACRONYMS

1. N_aOH

8. ASTM

Sodium hydroxide Poly lactic acid 2. PLA 3. ULT Un treated luffa fiber Treated luffa fiber 4. TLT 5. FTIR Fourier-Transform Infrared Spectroscopy Polypropylene 6. PP Polyvinyl Chloride 7. PVC

9. ISO International Organization For standards

American Society for Testing and Materials

Polyethylene Terephthalate 10. PET

Ultraviolet 11. UV

LIST OF TABLES

- Table 1: Fabrication methods.
- Table 2: Composition of luffa fibers.
- Table 3: Physical properties of luffa fibers.
- Table 4: Properties of different polymers.
- Table 5: Properties of polylactic acid.
- Table 6: Actual and coded factors for experimental design.
- Table 7: Experiment design of luffa fiber treated with 5% sodium hydroxide solution and PLA.
- Table 8: Percentage of Lignin removed.
- Table 9: Average percentage of Lignin removed.
- Table 10: Water absorption and Moisture content.
- Table 11: Water absorption and Moisture content for ULF/PLA.
- Table 12: Tensile Strength results.
- Table 13: Flexural strength result.
- Table 14: Weight loss percentage.

LIST OF FIGURES

Figure 01: Conceptual Frame work.

Figure 02: Luffa fibers.

Figure03: Polylactic acid.

Figure04: Chemical formula of polylactic acid.

Figure 05: Polymerization of a cyclic lactic dimer.

Figure06: General polymerization of lactic acid.

Figure 07: Solution preparation.

Figure 08: Fabrication process.

Figure 09: Water absorption Test.

Figure 10: Samples For Tensile Strength Test.

Figure 11: Tensile Strength Test.

Figure 12: Flexural Strength Test.

Figure 13: Burying Test of Luffa/PLA composite.

Figure 14: Percentage of lignin removed with concentration of NaOH

Figure 15: FTIR Spectroscopy.

Figure 16: Water absorbability and moisture regain of composite of different untreated luffa fiber content.

Figure 17: Tensile Strength of TLF and UTLF

Figure 18: Flexural strength.

Figure 19: Fracture analysis.

D	\mathbf{E}	CI	. 4	R	A	ГΤ	O	N	Ī

We hereby affirm that this final year project report is, to the best of our knowledge, the result of our research and work, and that it has never been offered or submitted to any organization or university for an academic award.

OCHAR JAMES
Signature
Date 11/09/2023
NAMBOZO SARAH GIFT
Signature
Date

DEDICATION

I Ochar James dedicate this report to My beloved parents, Uncle and other relative who have worked tirelessly to support me in my academic journey.

I Nambozo Gift Sarah dedicate this report to My beloved parents relatives and friends who endlessly supported and motivated me towards my goal and throughout the project proposal. We also thank my dear friends, course mates for their cooperation and lastly our supervisors who patiently and wisely handled us throughout the research project.

APPROVAL

This report has been submitted to the department of Polymer Textile and Industrial Engineering with the approval of the following supervisors.

Name Dr. NIBIKORA LDEPHONE
Name Dr. NIBIKORA LAZPHOWET
Dane 11/9/2093
į (į
Name & EDWIN KAMILHA
Signature II 57 1 70 23
Date
DAN TIGALANA
- Cossessor
Signature 11 00 2002

TABLE OF CONTENT

ABSTRACT	
ACKNOWLEDGEMENT	ii
LIST OF ACRONYMS	iii
LIST OF TABLES	iv
LIST OF FIGURES	v
DECLARATION	vi
DEDICATION	vii
APPROVAL	viii
1 CHAPTER ONE:	1
1.1 INTRODUCTION	1
1.2 BACKGROUND OF THE STUDY	2
1.3 PROBLEM STATEMENT.	3
1.4 OBJECTIVES	3
1.4.1 Main objective	3
1.4.2 Specific objectives	3
1.5 RESEARCH QUESTIONS	3
1.6 SIGNIFICANCE OF THE STUDY.	3
1.7 JUSTIFICATION OF THE STUDY	4
1.8 SCOPE OF THE STUDY	4
1.8.1 Geographical scope	4
1.8.2 Conceptual Scope	4
1.8.3 Conceptual framework	5
Figure 01: Conceptual Frame work	5
1.8.4 Time scope	5
2 CHAPTER TWO: LITERATURE REVIEW	6
2.1 BIOCOMPOSITE	6

	2.1.1	Development of Bio-composites
	2.1.2	Manufacturing methods
	Table 1:	Fabrication methods8
2	.2 LUI	FFA FIBER9
	Figure (02 : Luffa fibers10
	2.2.1	Composition of Luffa fiber
	Table 2:	Composition of luffa fibers11
	2.2.2	Luffa fiber properties
	Table 3:	Physical properties of luffa fibers11
2	.3 POI	LYLACTIC ACID12
	Figure0	3: Polylactic acid12
	Figure0	4: Chemical formula of polylactic acid13
	Figure0	5: Polymerization of a cyclic lactic dimer13
	2.3.1	Polymerization
	Figure0	6: General polymerization of lactic acid14
	2.3.2	Structure and properties of PLA
	Table 4:	Properties of different polymers15
	Table 5:	Properties of polylactic acid
	СНАРТ	TER THREE: METHODOLOGY
3	.1 ME	THODOLOGY 117
	3.1.1	Materials used,
	3.1.2	Extraction process
	3.1.3	Chemical modification of luffa fibers using alkaline treatment
	3.1.3.	1 Preparation of the solution,
	Figure (07 : Solution preparation
	3.1.3.	2 Procedures followed,
	3.1.4	Water bath preparation,

3

3.1.5 Fibre preparation,	18
3.1.6 CHARACTERIZATION OF LUFFA FIBERS	19
3.1.6.1 FTIR spectroscopy	19
METHODOLOGY 2,	19
3.2.1 To fabricate a bio composite and determine the effect of fiber load	ling on the
properties of the bio composite	19
3.2.2 Materials used,	19
3.2.3 Procedure,	19
Figure08: Fabrication process.	20
Table 6: Actual and coded factors for experimental design	20
Table 7: Experiment design of luffa fiber treated with 5% sodium hydroxide so	olution and
PLA	20
3.2.4 Effect of fiber loading on the properties of the luffa/PLA bio composit	te20
3.2.4.1 Moisture Content Measurement, ASTM D4442	20
3.2.4.2 Water absorption test: ASTM D570.	21
Figure09: Water absorption Test	21
Mechanical Properties Of Luffa Fiber- Polylactic Acid Composite	21
3.3.1 luffa fiber- PLA bio composite- Tensile strength test	21
3.3.1.1 Tensile test equipment	22
Figure 10: Samples For Tensile Strength Test	23
Figure 11: Tensile Strength Test.	23
3.3.2 luffa/PLA bio composite- flexural test	23
Figure 12: Flexural Strength Test	24
METHODOLOGY 3,	24
3.4.1 To assess the sustainability of the bio composite	24
Figure 13: Burying Test of Luffa/PLA composite	
CHAPTER FOUR RESULTS AND DICUSSIONS	26

4.1	Effect of alkaline treatment on luffa fibers	26
T_{i}	Table 8: Percentage of Lignin removed.	26
T_{i}	Table 9: Average percentage of Lignin removed	27
F	Figure 14: Percentage of lignin removed with concentration of NaOH	27
F	Figure 15: FTIR Spectroscopy.	28
4.2	Water absorptivity	29
T_{i}	Table 10: Water absorption and Moisture content	29
T_{i}	Table 11: Water absorption and Moiture content for ULF/PLA	30
	Figure 15: Water absorbability and moisture content of composite of different tre	
	Figure 16: Water absorbability and moisture regain of composite of different untre	
4.3	Effect Of Luffa Fiber Loading On The Mechanical Properties Of The	Bio
Con	mposite	31
4	2.3.1 Effect on Tensile strength	31
T_{i}	Table 12: Tensile Strength results	32
F	Figure 17: Tensile Strength of TLF and UTLF	32
4	2.3.2 Effect on Flexural strength.	33
T_{i}	Table 13: Flexural strength result	33
F	Figure 18: Flexural strength	34
4	.3.3 Fracture analysis.	34
F	Figure 19: Fracture analysis	34
4	.3.4 Suitability for the application	35
4.4	To assess the sustainability of the bio composite.	35
T_{i}	Table 14: Weight loss percentage	35
C	CHAPTER FIVE: CONCLUSIONS, CHALLENGES AND RECOMENDATIONS.	36
5.1	Conclusion	36
5.2	Challenges	36

5

5.3	Recommendations	37
<i>5</i> 4	DEFEDENCES	26
5.4	REFERENCES:	38
6 A	PPENDIX	41

1 CHAPTER ONE:

1.1 INTRODUCTION

In the pursuit of sustainable and eco-friendly construction materials, there has been a growing interest in the development of innovative solutions that address both environmental concerns and functional requirements. One such avenue of exploration is the creation of bio-composite materials, which combine natural fibers with biodegradable polymers to yield versatile, ecoconscious alternatives for traditional construction components(Bosák & Palko, 2019). This study explores the fascinating field of developing a bio-composite material for use in partition walls using luffa fiber and polylactic acid (PLA), exhibiting the potential to transform interior architecture with a focus on sustainability. Luffa fiber, sourced from the matured inner fibrous structure of the luffa gourd, offers an intriguing opportunity as a natural reinforcement in composite materials(Alhijazi et al., 2020). It boasts several attributes that make it a viable candidate for construction applications, including its lightweight nature, inherent strength, and renewability. On the other hand, polylactic acid (PLA), derived from renewable resources such as corn starch or sugarcane, presents an environmentally conscious choice as a biodegradable and compostable polymer(Kamran et al., 2022). Partition walls, being integral components of interior spaces, play a pivotal role in providing privacy, spatial organization, and noise separation. However, the conventional materials used for partition walls, such as gypsum board or concrete, often come with environmental drawbacks and limited design flexibility(Maneschi & Melhado, 2010). The interaction between luffa fiber and PLA holds the promise of overcoming these limitations by offering a sustainable solution that combines the advantages of both materials. Conclusion: By combining the durability of natural fibers with the environmentally friendly properties of biodegradable polymers, this research aims to contribute to the ongoing transformation of the construction industry into a greener, more responsible sector. The development of a luffa fiber/PLA bio-composite material for partition wall applications represents a significant step towards sustainable construction practices.

5.4 REFERENCES:

- Adeyanju, C. A., Ogunniyi, S., Ighalo, J. O., Adeniyi, A. G., & Abdulkareem, S. A. (2021). A review on Luffa fibres and their polymer composites. *Journal of Materials Science*, 56(4), 2797–2813. https://doi.org/10.1007/s10853-020-05432-6
- Alhijazi, M., Safaei, B., Zeeshan, Q., Asmael, M., Eyvazian, A., & Qin, Z. (2020). Recent developments in Luffa natural fiber composites: Review. *Sustainability (Switzerland)*, 12(18), 1–25. https://doi.org/10.3390/su12187683
- Alsuwait, R. B., Souiyah, M., Momohjimoh, I., Ganiyu, S. A., & Bakare, A. O. (2023).

 Recent Development in the Processing, Properties, and Applications of Epoxy-Based

 Natural Fiber Polymer Biocomposites. *Polymers*, *15*(1).

 https://doi.org/10.3390/polym15010145
- Bosák, L., & Palko, M. (2019). Wall Panel Made of Bio-composites. *MATEC Web of Conferences*, 279, 02010. https://doi.org/10.1051/matecconf/201927902010
- Chandra BhaskarBhaskar Chandra KandpalBhaskar Chandra KandpalRakesh ChaurasiaVishal Khurana. (2015). (7) (PDF) Recent Advances in Green Composites A Review. *International Journal For Technological Research In Engineering (IJTRE)*, 2(April), 1–7.
- Chen, Y., Su, N., Zhang, K., Zhu, S., Zhu, Z., Qin, W., Yang, Y., Shi, Y., Fan, S., Wang, Z., & Guo, Y. (2018). Effect of fiber surface treatment on structure, moisture absorption and mechanical properties of luffa sponge fiber bundles. *Industrial Crops and Products*, 123(June), 341–352. https://doi.org/10.1016/j.indcrop.2018.06.079
- Daniel-Mkpume, C. C., Ugochukwu, C., Okonkwo, E. G., Fayomi, O. S. I., & Obiorah, S. M. (2019). Effect of Luffa cylindrica fiber and particulate on the mechanical properties of epoxy. *International Journal of Advanced Manufacturing Technology*, 102(9–12), 3439–3444. https://doi.org/10.1007/s00170-019-03422-w
- Drumright, R. E., Gruber, P. R., & Henton, D. E. (2000). Polylactic acid technology. In *Advanced Materials* (Vol. 12, Issue 23). https://doi.org/10.1002/1521-4095(200012)12:23<1841::AID-ADMA1841>3.0.CO;2-E
- et al., 2005 Mohanty. (2016). 事業所における定期健康診断受診者の 健康習慣実行度とストレス反応の因子構造一健康習慣指数と職業性ストレス反応の主成分分析を試みて一 田甫久美子View metadata, citation and similar papers at core.ac.uk. *PENGARUH PENGGUNAAN PASTA LABU KUNING (Cucurbita Moschata) UNTUK*

- SUBSTITUSI TEPUNG TERIGU DENGAN PENAMBAHAN TEPUNG ANGKAK DALAM PEMBUATAN MIE KERING, 15(1), 165–175.
- Garlotta, D. (2001). A literature review of poly(lactic acid). *Journal of Polymers and the Environment*, 9(2), 63–84.
- Gottfridsson, M., & Zhang, Y. (2015). Environmental impacts of shoe consumption. 96.
- Jawaid, M., & Composites, F. (2019). Acoustic and mechanical properties of luffa fiber-reinforced biocomposites This is a post-refereeing final draft. When citing, please refer to the published version: mechanical properties of luffa fiber-reinforced Mohamed Thariq, Naheed Saba, In Wood. 325–341.
- Kamran, M. J., Jayamani, E., Heng, S. K., Wong, Y. C., Rahman, M. R., Al-Bogami, A. S., Huda, D., Bakri, M. K. Bin, & Rahman, M. M. (2022). Characterization and Comparative Study on Chemically Treated Luffa Fiber as Reinforcement for Polylactic Acid Bio-composites. In *BioResources* (Vol. 17, Issue 2, pp. 2576–2597). https://doi.org/10.15376/biores.17.2.2576-2597
- Li G., Zhao, M., Xu F., Yang B., Li X., Meng X., & Teng L. (2020). Synthesis and Biological Application of. *Molecules*, 25(5023), 1–18.
- Lopes, M. S., Jardini, A. L., & Filho, R. M. (2014). Synthesis and characterizations of poly (lactic acid) by ring-opening polymerization for biomedical applications. *Chemical Engineering Transactions*, 38, 331–336. https://doi.org/10.3303/CET1438056
- Maneschi, K., & Melhado, S. (2010). Scope of design for production of partition walls and facade coverings. *Architectural Engineering and Design Management*, 6(1), 3–17. https://doi.org/10.3763/aedm.2009.0098
- Mateus, R., Neiva, S., Bragança, L., Mendonça, P., & Macieira, M. (2013). Sustainability assessment of an innovative lightweight building technology for partition walls Comparison with conventional technologies. *Building and Environment*, 67, 147–159. https://doi.org/10.1016/j.buildenv.2013.05.012
- Mowafi, S., Taleb, M. A., & Industries, T. (2018). *Utilization of Proteinic Biopolymers:**Current Status and Future Prospects. 15.

 https://doi.org/10.21608/JTCPS.2018.5007.1002
- Pang, X., Zhuang, X., Tang, Z., & Chen, X. (2010). Polylactic acid (PLA): Research, development and industrialization. *Biotechnology Journal*, *5*(11), 1125–1136. https://doi.org/10.1002/biot.201000135

- Partap, S., Kumar, A., Sharma, K., & Jha, K. K. (2012). Luffa Cylindrica: An important medicinal plant. *J. Nat. Prod. Plant Resour*, 2012(1), 127–134.
- Puri, V., Chakrabortty, P., Anand, S., & Majumdar, S. (2017). Bamboo reinforced prefabricated wall panels for low cost housing. *Journal of Building Engineering*, *9*, 52–59. https://doi.org/10.1016/j.jobe.2016.11.010
- Ranakoti, L., Gangil, B., Misha, S. K., Singh, T., Sharma, S., A., I. R., & El-khatib, S. (2022). Critical Review on Polylactic Acid: Properties, Structure, *Materials*, *15*(4312), 1–29.
- Randall, J. (2022). *Polylactic Acid Technology* (Issue April 2005). https://doi.org/10.1201/9780203508206.ch16
- Robert, B., & Brown, E. B. (2004). *No* 主観的健康感を中心とした在宅高齢者における 健康関連指標に関する共分散構造分析Title. I, 1–14.
- Sengupta, A., Pattnaik, S., & Sutar, M. K. (2017). *Biocomposites: An Overview.* 4(8), 648–653.
- Shukla, P. (2022). Biocomposites: Fabrication, Properties, and Applications A Review, Biocomposites: Fabrication, Properties, and Applications A Review, October 2014.
- Vasconcelos, G., Lourenço, P. B., Mendonça, P., Camões, A., Mateus, R., Bragança, L., Brito, A. G., & Poletti, E. (2013). Proposal of an innovative solution for partition walls: Mechanical, thermal and acoustic validation. *Construction and Building Materials*, 48, 961–979. https://doi.org/10.1016/j.conbuildmat.2013.07.079
- Wei, L., & McDonald, A. G. (2016). A review on grafting of biofibers for biocomposites. *Materials*, 9(4). https://doi.org/10.3390/ma9040303
- Zahid Rayaz Khan, M., & Srivastava, S. K. (2018). Development, Characterization and Application Potential of Bio-composites: A Review. *IOP Conference Series: Materials Science and Engineering*, 404(1). https://doi.org/10.1088/1757-899X/404/1/012028
- Zaman, H. U., Song, J. C., Park, L., Kang, I., Park, S., Kwak, G., Park, B., & Yoon, K. (2011). Poly (lactic acid) blends with desired end-use properties by addition of thermoplastic polyester elastomer. 187–198. https://doi.org/10.1007/s00289-011-0448-5